

8 MIL CLEAR

Performance Data

Total Solar Energy Rejected	20%
Solar Energy Reflected	10%
Solar Energy Absorbed	14%
Solar Energy Transmitted	76%
Visible Light Transmitted	84%
Visible Light Reflected	10%
Ultra Violet Light Rejected	93%
Shading Coefficient	0.92
Solar Heat Gain Coeff. (g Value)	-
Emissivity	-
Glare Reduction	5%

Mechanical Properties

Thickness	200 micron	Peel Strength	7 lb/inch
Tensile Strength at Break	28,500 psi	Ply	2
Break Strength	224 lb/inch	EN12600	1B1
Elongation at Break	125%		

Performance Guide

Solar Heat Rejection	★ ☆ ☆ ☆ ☆
Glare Reduction	☆ ☆ ☆ ☆ ☆
UV Reduction	★ ★ ★ ★ ☆
Fade Reduction	★ ☆ ☆ ☆ ☆
Safety & Security	★ ★ ★ ★ ★
One-Way Privacy	☆ ☆ ☆ ☆ ☆
Two-Way Privacy	☆ ☆ ☆ ☆ ☆
Scratch Coating	Yes
Warranty Period	10 Years

Key: Excellent - ★★★★★ Some Benefit - ★☆☆☆☆ N/A - ☆☆☆☆☆

